


ACETex® ES-Series woven geotextiles, fabricated with self-developed high tenacity polypropylene yarns and well-designed texture, perform exceptionally well in separation, filtration, and reinforcement functions altogether to enhance the safety, reliability and serviceability of paved and unpaved roadways. With high tensile strength (biaxial tensile strengths up to 200 kN/m) and modulus of the geotextiles, which provide structural stability and distribute load uniformly at low elongation to increase the load-carrying capacity of the system, the ACETex® ES-Series are commonly placed between road base and subgrade. Furthermore, by increasing permeability with appropriate pore sizes, ACETex ES-Series achieve separation and filtration simultaneously to stabilize the structure of the roadway system in the long term. Moreover, ACETex[®] ES-Series are available in various tensile strengths and hydraulic properties to meet diverse project engineering needs.

APPLICATIONS


Roadway / Railway

- Subgrade Stabilization
- Base Reinforcement




Embankment

· Soft Foundation Stabilization




BENEFITS from the Integrated FUNCTIONS of the Product

Reinforcement



- · Increase bearing capacity
- Add membrane support
- Provide lateral restraint

Separation & Filtration



- Prevent mixture of base course and subgrade materials
- Retain fine particles
- Mitigate waterbed effect

Safety

Reduce rutting

Reduce inhomogeneous settlement

Improve trafficability

Economical

Extend roac service life

Reduce required base course materials

Lower maintenance costs

Applicability

Use in heavy rainfall/ high water table areas

Use with some difficult soils

Allow permeable bavement systems

ACETex® ES-Series woven geotextiles

for Base Reinforcement and Subgrade Stabilization

ACE Geosynthetics is dedicated to developing and manufacturing geotextiles, and providing wide technical service in the realm of geotechnical engineering for decades. The experience and expertise accumulated in these activities are the key factors to make ACETex[®] ES Series successful products, which are well-functional, reliable, and durable with high cost-effectiveness.





Mechanical Index Properties	SI Unit	ES420	ES510	ES520	ES710	ES720	ES815	Test
Tensile strength at 2% strain-MD	kN/m	9	10	10	10	7	10	ASTM D4595
Tensile strength at 2% strain-CD	kN/m	10	10	20	20	30	25	ASTM D4595
Tensile strength at 5% strain-MD	kN/m	24	25	30	35	21	25	ASTM D4595
Tensile strength at 5% strain-CD	kN/m	30	25	40	45	70	65	ASTM D4595
Mechanical Performance Properties			广					
UV Resistance -Retained Strength(500 hr)	%	90	90	90	90	90	90	ASTM D4355
Hydraulic Properties			~(
Permittivity (50mm head) Apparent Opening Size(O95)	1/sec mm	1 0.425	0.4 0.425	1 0.425	0.4 0.425	1 0.425	0.4 0.425	ASTM D4491 ASTM D4751

Note

The values given are indicative and correspond to an average results obtained in our laboratories and testing institutes. The right is reserved to make changes without notice.

Disclaimer:

This document is provided solely for general information, and shall not be construed as engineering advice, or part of the contract with any customer not withstanding anything to the contrary in the contract. We hereby disclaim any liability in connection with any use of the information herein.



Email: sales@geoace.com Tel: +886 4 2659 5926 Fax: +886 4 2659 5935





