

BITUMEN 60/70

DESCRIPTION:

Bitumen 60/70 is a standard Penetration Grade of Bitumen ASTM D946M, typically used as a Paving Grade Bitumen suitable for road construction and for the production of asphalt pavements with superior properties particularly in road and airport constructions and other similar applications. This grade of Bitumen is mainly used in the manufacture of hot mix asphalt for bases and wearing courses. Penetration Grades of Bitumen is produced from Vacuum Residue, which is blown by hot air in the blowing unit; The fully automated process runs continuously resulting in a constant and homogeneous finished product quality. Penetration Grade Bitumen can be supplied in any grade and are designated by two numbers to indicate the mid-points of their penetration ranges.

PACKAGING:

Paving Bitumen is commonly packed in new steel drums, 150, 180 & 220 Kg barrels and Jumbo Bags or Flexi tank.

CHARACTERISTICS AND SPECIFICATIONS:

Bitumen Grade 60/70 is produced in compliance and conformity to International Standards such as AASHTO M20-70 & ASTM D946, also, meets the following specification requirements.

SPECIFICATIONS	UNIT	STANDARD	MIN	MAX
Penetration	dmm.	ASTM D5	60	70
Softening Point	°C	ASTM D36	49	56
Specific Gravity	Gr/Cm ³	ASTM D70	1.01	1.06
Flash Point	°C	ASTM D92	230	–
Ductility at 25°C	Cm	ASTM D113	100	–
Solubility In Trichloroethylene	WT %	ASTM D2042	99	100
Loss On Heating	WT %	ASTM D6	–	1
Drop In Penetration After Heating	%	ASTM D6	–	20
After Thin-Film Oven Test (TFOT) ASTM D1754				
Retained Penetration	%	ASTM D5	52	–
Increase In Softening Point	°C	ASTM D36	–	10
Ductility	Cm	ASTM D113	50	–
Spot Test	A.A.S.H.T.O.102		Negative	